

OUR PRODUCTS

Gypsum Plaster



Smooth
Finish



Less Paint
Consumption

IS : 2547



PART-I

CM/L-3023835

General Specifications:

Setting Time	15-20 min.
Residue	4% – 5%
Whiteness	70% – 72%
ISO Certified	Yes
ISI Certified	Yes
Wastage	NIL
Transverse Strength (kg/cm ²)	16-20
Compressive Strength (N/mm ²)	2-4
Density (kg/m ³)	750-800
Chemical Composition	Calcium Sulphate Hemihydrate [CaSO ₄ .1/2H ₂ O]
Water to Material Ratio	1 : 1.25
Coverage (1kg)	1 sq.ft. with 12mm thickness
Shelf Life	12 months From the date of manufacturing, when stored in dry conditions.

Note: Mix powder in water, not vice versa.
(*All tested results are under lab condition)



Packaging : 1kg, 2kg, 20kg, 25kg & 40kg

Gypsum Plaster



**Super White &
Super Strength**



**Extra
Coverage**



**Made From Indian
& Imported Gypsum**



**Special Power
Packing**

General Specifications:

Setting Time	15-20 min
Residue	2% – 4%
Whiteness	74% – 78%
ISO Certified	Yes
ISI Certified	Yes
Wastage	NIL
Transverse Strength (kg/cm ²)	18 -22
Compressive Strength (N/mm ²)	3 - 5
Density (kg/m ³)	700-750
Chemical Composition	Calcium Sulphate Hemihydrate [CaSO ₄ .1/2H ₂ O]
Water to Material Ratio	1 : 1.25
Coverage (1kg)	1.25 sq. ft. with 12 mm thickness
Shelf Life	12 months From the date of manufacturing, when stored in dry conditions.

IS : 2547

PART-I
CM/L-3023835



Packaging : 25kg

Note: Mix powder in water, not vice versa.
(*All tested results are under lab condition)

Gypsum Plaster



**Super White &
Super Strength**



**Extra
Coverage**



**Smooth
Finish**



**Less
Residue**

General Specifications:

Setting Time	15-20 min
Residue	2% – 4%
Whiteness	76% – 80%
ISO Certified	Yes
ISI Certified	Yes
Wastage	NIL
Transverse Strength (kg/cm ²)	18 -22
Compressive Strength (N/mm ²)	3 - 5
Density (kg/m ³)	700-750
Chemical Composition	Calcium Sulphate Hemihydrate [CaSO ₄ .1/2H ₂ O]
Water to Material Ratio	1 : 1.25
Coverage (1kg)	1.25 sq. ft. with 12 mm thickness
Shelf Life	12 months From the date of manufacturing, when stored in dry conditions.

IS : 2547

 PART-I
 CM/L-3023835

Special
Nozzle
Packing



Note: Mix powder in water, not vice versa.
 (*All tested results are under lab condition)

Packaging : 25kg